

VISCOM - PROMOTIONAL

Issue date : 18/04/2013  
Date last modification : 18/11/2014

## 08423 RI-FIX PVC GLOSS WHITE ARS3 ULTRAREMOVABLE WK140

### Face Material

Gloss white monomeric soft vinyl.

Type	Monomeric vinyl
Colour and Finish	Gloss white
Weight	210 g/m <sup>2</sup> ±10% ISO-536
Thickness	170 µ ±10% ISO 534-80

### Adhesive

Solvent based ultraremovable adhesive featuring very low adhesion and easy and clean removability from plastics and glass substrates.

Reference	ARS3 ultraremovable
Type	Acrylic removable
Min. Appl. Temp.	+10°C
Service Temp.	-20°C/+100°C
Shear	High
Tack	Very low N/inch <sup>2</sup>
Final Adhesion	Very low N/inch

### Liner

Type	One side siliconised clay coated Kraft
Colour and Finish	White
Weight	135 g/m <sup>2</sup> ±10% PP-032 - ISO 536
Thickness	145 µ ±10% ISO 534
Transparency	n.a. % DIN 53 147-64

### Applications

Ideal for short to medium term window applications. Due to ultra removable repositioning adhesive, this product is suitable for application by any member of a retail team; however we recommend the product be applied to windows protected from external forces, for example: on the outside of a window but within a shopping mall.

### Printing Methods

Excellent print results with UV, solvent and eco-solvent ink-jet printing.  
Ritrama recommends leaving a 5% border around your graphic when printing.  
Ritrama recommends at least 24/48 hours of cure time before cutting  
Testing for suitability between media, printers and inks is always recommended prior to use.

### Shelf life

36 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.