

## Printable Gold Mirror vinyl

### NRSLPRINT/50

#### Description:

Film: 70micron PET vinyl, Gold  
 Adhesive: clear removable adhesive  
 Liner: 125micron dull polish PET release film  
 Width: 1.27 m

#### Features:

1. Fully compatible with inkjet printing, applicable to various printer models.
2. Stable ink absorption and excellent dimensional stability.
3. The ink dries quickly, and no ink blur.
4. The aluminized film has excellent metallic luster and the light reflectivity can reach over 92%.
5. Good anti-aging properties.

#### Applications:

1. Suitable for mobile media such as cars and subways, commercial billboards, signs, exhibition display ads, etc.
2. Suitable for Solvent, Eco-solvent, UV and Latex printing.

#### Technical Data:

Testing condition: Indoor temperature  $23\pm 2^{\circ}\text{C}$ . Relative humidity  $50\pm 5\%$ . Using aluminum, glass, steel plate as the base material for testing.

Test Items	Units	Test method	Average value
Thickness-film	Micron	GB/T6672-2001	$70\pm 10$
Weight-Liner	$\text{g}/\text{m}^2$	GB4669-1995	$175\pm 10$
Weight -finished product	$\text{g}/\text{m}^2$	GB4669-1995	$295\pm 20$
Gloss Rate 60	%	GB8807-88	$\geq 70$
Initial Adhesion	N/25mm	FTM 9	$\geq 8$
24h. 180 peel	N/25mm	FTM 1	$\geq 5$
Dimensional stability MD	mm	FTM 14	$\leq 0.8$
Dimensional stability CD	mm	FTM 14	$\leq 0.5$
Tensile strength MD	N/25 mm	GB/T1040.1-2006	$\geq 45$
Tensile strength CD	N/25 mm	GB/T1040.1-2006	$\geq 40$
Construction Temperature	$^{\circ}\text{C}$		$20\pm 10^{\circ}\text{C}$
Applicable Temperature	$^{\circ}\text{C}$		$-20 \sim +70$

\*All technical data is subject to change without prior notice.