

Technical Data Sheet

Evolution Whiteback Paper 140

Property			Units	Tolerance	
Substance	ISO 536	TAPPI T410	gsm	± 4%	140
Thickness	ISO 534	TAPPI T411	µm	± 7%	134
Caliper	ISO 534	TAPPI T411	Pt.	± 7%	5,3
Whiteness CIE	ISO 11475		%	± 3	101,5
Smoothness Bekk	ISO 5627	TAPPI T475	s	± 20	126
Cobb (uncoated side)	ISO 535		g/m ²	± 4	36
Opacity	ISO 2471	TAPPI T519	%	-2	99
Relative humidity		TAPPI T502	%	± 7	48

Suit for:

- ☒ Solvent inkjet
- ☒ Latex
- ☒ UV curable
- ☒ Screen printing
- ☐ Eco solvent inkjet
- ☒ Cold over laminating
- ☐ Water based inkjet
- ☐ Die Sublimation

Common Applications

- Point of purchase
- Outdoor advertising
- Indoor advertising
- Exhibition graphics